

## PRODUCT INFORMATION

# CEVO®-process J-4419

## Product Description

CEVO®-process J-4419 is a patented organic acid wax, based on renewable plant waxes. It combines in an ideal manner the characteristics of a multi-purpose plastics additive with the call for bio-based raw materials. It is therefore also perfectly suitable for thermoplastic polymers, that are derived from renewable resources. CEVO®-process J-4419 mainly consists of natural long-chain fatty acids (mainly C19 – C32) that have been processed by an innovative technology to give a bio-based polymer additive that meets the highest standards in the polymer industry.

## General Advantages

High effectiveness at low concentrations: CEVO®-process J-4419 is suitable for a wide range of plastics applications, mainly as external release agent, dispersing agent, gloss booster and surface improver. CEVO®-process J-4419 is suitable for engineering plastics, thermosets, etc.

## Examples of Use

- Thermoplastics: ABS and copolymers
- Thermosets: epoxy resins, phenolic resins
- Dispersing agents for colour masterbatches

## Delivery Specifications \*

Characteristics	Unit	Target value	Method
Acid value *	mg KOH/g	120 – 170	ISO 2114
Drop point *	°C	78 – 85	ASTM 3954
Colour	–	pale yellow	AA 3.2.1.505

## Packaging and Handling

Physical form	Flakes or powder
Packaging	Paper bag or Big Bag
Storage	Store at ambient temperature on a dry place. Protect from heat/overheating and direct sunlight. The maximum shelf life is 5 years after production. Thereafter, tests of the chemical characteristics are recommended. After delivery, a minimum remaining shelf life at the customer of 1.5 years is warranted.

## Safety

CEVO®-process J-4419

- is made from a renewable biological source
- reached the criteria for inherent biodegradability (OECD Guideline 301 D, Closed Bottle Test)
- is not classified as carcinogenic, mutagenic or reprotoxic; no health or environmental hazards are known, provided it is applied in industrial and professional settings

## Delivery Time and Availability

Standard delivery time: 2 – 3 weeks. Preconditions can be met for achieving shorter delivery times on standard products when demanded by the market.

## Legislation

Food contact legislation:

- Product for technical applications

Other legislation:

- Bio-based (100 %)
- REACH, RoHS and CONEG compliant
- TSCA (USA) and DSL (Canada): listed

For further information, please contact [application@voelpker.com](mailto:application@voelpker.com).